



# Chemical Consultants INCORPORATED

1850 Wild Turkey Circle Corona CA 92880 USA 951/735-5511 FAX 951/735-7999 www.ccidom.com

## A-MESH TECHNICAL TABLE

	Metric	Weave	Mesh opening	Thread diameter	Open area	Thickness	Ink volume cm3xm2	Recommended tension
25-200	10-200	1x1	816	200	65	440	276	42
40-200	16-200	1x1	435	200	47	420	189	42
53-140	21-140	1x1	340	140	50	250	125	42
60-120	24-120	1x1	300	120	51	210	105	42
86-70	34-70	1x1	245	70	61	100	56	35
86-100	34-100	1x1	210	100	45	165	70	35
110-80	43-80	1x1	150	80	41	130	55	35
122-70	48-70	1x1	135	70	41	115	46	32
137-64	54-64	1x1	115	64	39	102	40	30
150-55	59-55	1x1	100	55	40	93	39	32
150-64	59-64	1x1	95	64	32	100	35	32
155-64	61-64	1x1	90	64	32	106	35	32
173-55	68-55	1x1	80	55	30	90	30	28
196-48	77-48	1x1	78	48	30	84	24	28
196-55	77-55	1x1	70	55	25	88	24	28
230-48	90-48	1x1	55	48	25	78	20	33
254-40	100-40	1x1	58	40	32	65	21	27
280-40	110-40	1x1	48	40	27	65	17	30
305-34	120-34	1x1	45	34	30	55	16	27
305-40	120-40	1x1	40	40	20	55	16	26
355-31	140-31	1x1	35	31	26	48	13	25
355-34	140-34	1x1	30	34	20	55	10	30
380-34	150-34	1x1	30	34	20	69	10	30
380-31	150-31	1x1	32	31	23	47	10	26